

EMI 361 UV BLACK

PC-MEF(x)10

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	2413	MPa	ASTM D 638
Tensile Strength	61.4	MPa	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Flexural Strength	96.5	MPa	ASTM D 790
Izod Impact notched, 1/8 in	74.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	124	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	10	Ohm*cm	ASTM D 257
Other properties			
Density	1320	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	277 - 304	°C	-
Mold temperature	71.1 - 121	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

Increased electrical conductivity, U.V. stabilized or stable to weather

Features

EMI Attenuation/Shielding

Regional Availability

North America, Europe, Asia Pacific