

SKYPURA 0302

PCT

SK Chemicals

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	286	°C	ASTM D 3418
Glass Transition Temperature	89	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Intrinsic Viscosity	0.65	dl/g	-
Color L	88	-	CIE
Color a	0	-	CIE
Color b	6	-	CIE

Characteristics**Special Characteristics**

Light stabilized or stable to light, Heat stabilized or stable to heat

Features

Good Adhesion, Thermal Stability

Chemical Resistance

General Chemical Resistance

Certifications

Food contact

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America