

**SKYPURA 1631**

PCT

SK Chemicals

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>280</b>	°C	ASTM D 3418
Glass Transition Temperature	<b>89</b>	°C	ASTM E 1356

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Intrinsic Viscosity	<b>0.8</b>	dl/g	-
Color L	<b>88</b>	-	CIE
Color a	<b>0</b>	-	CIE
Color b	<b>6</b>	-	CIE

**Characteristics****Special Characteristics**

Heat stabilized or stable to heat, Transparent

**Certifications**

Food contact

**Features**

Good Adhesion, Thermal Stability

**Applications**

Electrical and Electronical

**Chemical Resistance**

General Chemical Resistance, Hydrolytically Stable

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America