

**SKYPURA 3502**

PCT

SK Chemicals

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melting Temperature	<b>286</b>	°C	ASTM D 3418
Glass Transition Temperature	<b>89</b>	°C	ASTM E 1356

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Intrinsic Viscosity	<b>0.75</b>	dl/g	-

**Characteristics****Special Characteristics**

Heat stabilized or stable to heat

**Features**

Good Adhesion, Thermal Stability

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Food contact

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America