

Product Texts

Durastar™ DS2110UVI polymer, contains an ultraviolet light stabilization package. It is recommended for indoor applications requiring enhanced color stability upon extended exposure to fluorescent light. It has excellent appearance and is nearly water-clear. Its other most outstanding features are toughness, chemical resistance, and excellent processing characteristics. DS2110UVI has very good toughness as shown by Izod impact resistance.

Easy to process, it flows readily, fills intricate molds, and contains a mold release.

This product is certified to ANSI/NSF Standard 51.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Yield stress	47	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	49	MPa	ISO 527
Strain at break	210	%	ISO 527
Flexural modulus, 23°C	1750	MPa	ISO 178
Flexural strength	64	MPa	ISO 178
Izod notched impact strength, +23°C	29.6	kJ/m ²	ISO 180/1A
Izod notched impact strength	6.3	kJ/m ²	ISO 180/1A
Temperature	-40	°C	-
Puncture energy, +23°C	71	J	ISO 6603-2
ASTM Data			
Tensile Strength at Yield	46	MPa	ASTM D 638
Tensile Strength at Break	53	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	310	%	ASTM D 638
Flexural Modulus	1900	MPa	ASTM D 790
Rockwell Hardness	105	-	ASTM D 785
Izod Impact notched, 1/8 in	370	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	60	J/m	ASTM D 256
Temperature	-40	°C	-
Izod Impact unnotched, 1/8 in	N	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	66	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	73	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	73	°C	ASTM D 648
DTUL @ 264 psi	65	°C	ASTM D 648
Optical properties			
ASTM Data			
Haze	0.3	%	ASTM D 1003
Light Transmittance	91	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ISO 1183
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70	°C	-
Pre-drying - Time	3	h	-
Melt temperature	250 - 290	°C	-
Mold temperature	15 - 30	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Additives

Release agent

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather, Transparent

Features

Color Stability

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval NSF 51

Applications

Refrigeration, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa