

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>45</b>	g/10min	ISO 1133
Temperature	<b>300</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>0.7</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>0.7</b>	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>45</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>2.16</b>	kg	-
Mold Shrinkage, MD	<b>0.0065</b>	mm/mm	ASTM D 955
Mold Shrinkage, TD	<b>0.0065</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>4500</b>	MPa	ISO 527
Yield stress	<b>65</b>	MPa	ISO 527
Stress at break	<b>65</b>	MPa	ISO 527
Strain at break	<b>1.7</b>	%	ISO 527
Flexural modulus, 23°C	<b>6700</b>	MPa	ISO 178
Flexural strength	<b>95</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>4</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	<b>3</b>	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	<b>R 118</b>	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Modulus	<b>4800</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>73</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>73</b>	MPa	ASTM D 638
Elongation at Break	<b>2.2</b>	%	ASTM D 638
Flexural Modulus	<b>6400</b>	MPa	ASTM D 790
Flexural Strength	<b>110</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 118</b>	-	ASTM D 785
Izod Impact unnotched, 1/8 in	<b>250</b>	J/m	ASTM D 256
Izod Impact unnotched, 1/4 in	<b>190</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>250</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>250</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1610</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1610</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Extrusion</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>100</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Processing humidity	<b>≤0.06</b>	%	-
Mold temperature	<b>50 - 140</b>	°C	-
Zone 1	<b>290 - 300</b>	°C	-

**INFINO TK-2046P**

PCT-GF

Lotte Chemical Corporation

Zone 2	<b>300</b>	°C	-
Zone 3	<b>305 - 310</b>	°C	-
Nozzle temperature	<b>305 - 310</b>	°C	-

**Characteristics****Processing**

Other Extrusion

**Delivery form**

Pellets, Natural Color

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific