

Product Texts

Base Polymer	Polycarbonate
Filler/Additive System	15 % special filler
Special Features	highly reflective,opaque,easy release (demoulding),injection moulding grade,UV stabilised
Market Segment	Automotive,various
Application Area	lighting,light blocking components
Typical Applications	light guides,reflectors

Processing/Physical Characteristics

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Tensile Modulus	2900	MPa	ISO 527
^[C] Yield stress	63	MPa	ISO 527
^[C] Yield strain	5.6	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Temp. of deflection under load, 1.80 MPa	129	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	140	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
--	-------	------	---------------

^[C] Density	1360	kg/m ³	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Light Blocking

Delivery form

White

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Special Characteristics

U.V. stabilized or stable to weather

Other text information**Injection molding**

Pre-Drying Conditions

120 °C in a dry air (dessiccant) dryer
for 2-4 h

120 °C in an air circulating dryer
for 4-12 h

max. moisture content <0,02 %

Processing Injection Moulding melt temperature 280-320 °C
mould temperature 80-110 °C

Storage dry, protected from light