

Product Texts

Base Polymer	Polycarbonate
Filler/Additive System	special filler,UV stabilised
Special Features	translucent,light scattering,high light diffusion
Market Segment	Automotive,Lighting
Application Area	light transparent components,Black Panel-Technology
Typical Applications	display elements,operating elements

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

^[C] Melt volume-flow rate, MVR	20	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

Mechanical properties**Value****Unit****Test Standard****ISO Data**

^[C] Tensile Modulus	2400	MPa	ISO 527
^[C] Yield stress	66	MPa	ISO 527
^[C] Yield strain	6	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties**Value****Unit****Test Standard****ISO Data**

^[C] Temp. of deflection under load, 1.80 MPa	124	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	142	°C	ISO 306

[C]: CAMPUS

Other properties**Value****Unit****Test Standard**

^[C] Density	1190	kg/m ³	ISO 1183
------------------------	-------------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Light Diffusing

Delivery form

Black

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather, Translucent

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions 120 °C in a dry air (dessiccant) dryer
 for 2-4 h
 120 °C in an air circulating dryer
 for 4-12 h
 max. moisture content <0,02 %

Processing Injection Moulding melt temperature 270-310 °C
 mould temperature 80-110 °C

Storage dry, protected from light