

CX-02WH

PC

Next Polymers Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.3	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.004	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2300	MPa	ASTM D 638
Tensile Strength	62	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	92	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	589	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	98.1	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	70	E-6/K	ASTM D 696
DTUL @ 66 psi	145	°C	ASTM D 648
DTUL @ 264 psi	128	°C	ASTM D 648
Vicat Temperature	140	°C	ASTM D 1525
Thermal Conductivity, solid state	0.0288	W/(m K)	ASTM C 177

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	20	kV/mm	IEC 60243-1
ASTM Data			
Dielectric Constant, 60 Hz	3	-	ASTM D 150

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.3	%	ASTM D 570
Water Absorption, Equilibrium	0.35	%	ASTM D 570
Density	1200	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

White

Special Characteristics

Heat stabilized or stable to heat

Applications

Electrical and Electronical, Encapsulation

Regional Availability

Asia Pacific