

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	23	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	64	MPa	ISO 527
Stress at break	64	MPa	ISO 527
Strain at break	110	%	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Flexural strength	92	MPa	ISO 178
Charpy notched impact strength, +23°C	60	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	R 120	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Modulus	2300	MPa	ASTM D 638
Tensile Strength at Yield	63	MPa	ASTM D 638
Tensile Strength at Break	63	MPa	ASTM D 638
Elongation at Break	110	%	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	90	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	740	J/m	ASTM D 256
Izod Impact notched, 1/4 in	98	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	120	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	132	°C	ISO 75-1/-2
Vicat softening temperature, B	140	°C	ISO 306
<b>ASTM Data</b>			
DTUL @ 66 psi	132	°C	ASTM D 648
DTUL @ 264 psi	122	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1200	kg/m <sup>3</sup>	ISO 1183
Density	1200	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	290 - 300	°C	-
Mold temperature	80 - 120	°C	-
Zone 2	250 - 270	°C	-
Zone 3	270 - 300	°C	-
Nozzle temperature	300	°C	-

**INFINO MR-1020**

PC

Lotte Chemical Corporation

Screw speed	<b>120 - 130</b>	rpm	-
Injection pressure	<b>6.4</b>	MPa	-
Back pressure	<b>1.5</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Medical

**Delivery form**

Pellets, Natural Color

**Regional Availability**

North America, Europe, Asia Pacific