

INFINO UF-1017B

PC

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	28	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
ASTM Data			
Melt Flow Index, MFI	28	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2200	MPa	ISO 527
Yield stress	61	MPa	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	52	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	95	MPa	ISO 178
Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	14	kJ/m ²	ISO 180/1A
Rockwell hardness	R 120	-	ISO 2039-2
ASTM Data			
Tensile Strength at Yield	61	MPa	ASTM D 638
Flexural Modulus	2400	MPa	ASTM D 790
Flexural Strength	89	MPa	ASTM D 790
Izod Impact notched, 1/8 in	590	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	91	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	103	°C	ISO 75-1/-2
Vicat softening temperature, B	109	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.7	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.7	mm	-
Other properties			
Density	1190	kg/m ³	ISO 1183
Density	1190	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.05	%	-
Melt temperature	280	°C	-
Mold temperature	40 - 120	°C	-
Zone 1	220 - 230	°C	-
Zone 2	240 - 280	°C	-
Zone 3	260 - 300	°C	-
Nozzle temperature	280	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	49 - 250	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Applications

Electrical and Electronical

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific