

KCA9360

PC

Shanghai Kumho Sunny Plastics Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	53	MPa	ASTM D 638
Flexural Modulus	2000	MPa	ASTM D 790
Flexural Strength	68	MPa	ASTM D 790
Izod Impact notched, 1/8 in	700	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	125	°C	ASTM D 1525
Other Standards^[S]			
Glow Wire Flammability Index (GWFI)	750	°C	IEC 60695-10-2

S: These properties are reported by the producer according standards that are different to our defaults.

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E15	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1210	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	230 - 260	°C	-
Mold temperature	50 - 90	°C	-

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical

Regional Availability

Asia Pacific