

Product Texts

ELCRIN EXL1213TB polycarbonate (PC) siloxane copolymer is transparent injection molding grade with major component synthesized from Bio source. This grade offers extreme low temperature ductility in combination with high flow characteristics, excellent processability and good chemical resistance. It is a general purpose product available in transparent and opaque colors and is an excellent candidate for a broad range of applications.

UL Yellow Card Link: [E207780-104423784](https://www.ulprospector.com/207780-104423784)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	13.3	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
ASTM Data			
Melt Flow Index, MFI	14.7	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2080	MPa	ISO 527
Yield stress	56	MPa	ISO 527
Yield strain	5	%	ISO 527
Stress at break	56	MPa	ISO 527
Strain at break	80	%	ISO 527
Flexural modulus, 23°C	1950	MPa	ISO 178
Flexural strength	86	MPa	ISO 178
Charpy impact strength, +23°C, 3mm	94	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C, 3mm	95	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C, 3mm	53	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C, 3mm	21	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	132	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	53	kJ/m ²	ISO 180/1A
Izod notched impact strength	19	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
ASTM Data			
Tensile Modulus	2060	MPa	ASTM D 638
Tensile Strength at Yield	56	MPa	ASTM D 638
Tensile Strength at Break	53	MPa	ASTM D 638
Elongation at Yield	5.8	%	ASTM D 638
Elongation at Break	90	%	ASTM D 638
Flexural Modulus	2080	MPa	ASTM D 790
Flexural Strength	91	MPa	ASTM D 790
Izod Impact notched, 1/8 in	830	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	620	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	121	°C	ISO 75-1/-2
Vicat softening temperature, B	140	°C	ISO 306
Coeff. of linear therm. expansion, parallel	97	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	92	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.7	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94

Thickness tested	0.7	mm	-
Coefficient of Thermal Expansion, MD	84	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	90	E-6/K	ASTM D 696
DTUL @ 264 psi	119	°C	ASTM D 648
Vicat Temperature	147	°C	ASTM D 1525

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	89	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Humidity absorption	0.05	%	Sim. to ISO 62
Density	1180	kg/m ³	ISO 1183
Density	1180	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	290 - 320	°C	-
Mold temperature	80 - 115	°C	-
Zone 1	280 - 295	°C	-
Zone 2	285 - 305	°C	-
Zone 3	295 - 320	°C	-
Nozzle temperature	290 - 310	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified, Transparent, Opaque

Features

Ductile, Copolymer

Chemical Resistance

General Chemical Resistance

Certifications

Contains renewable resources

Applications

Electrical and Electronical, General Purpose, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America