

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.007	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2410	MPa	ASTM D 638
Tensile Strength at Break	55.2	MPa	ASTM D 638
Elongation at Break	8	%	ASTM D 638
Flexural Modulus	2410	MPa	ASTM D 790
Flexural Strength	82.7	MPa	ASTM D 790
Izod Impact notched, 1/4 in	130	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.18	%	ASTM D 570
Density	1290	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Additives

Lubricants

Applications

IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa