

Product Texts

- (PC+ABS)-Blend
- easy flowing
- Vicat/B 120 temperature = 131 °C
- meet certain requirements of ISO Standard 10993-1
- for further information please contact plastics@covestro.com

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	25	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2500	MPa	ISO 527
^[C] Yield stress	62	MPa	ISO 527
^[C] Yield strain	4.9	%	ISO 527
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	48	kJ/m ²	ISO 180/1A
Izod notched impact strength	15	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	109	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	127	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	129	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	2.9	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	2.9	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	30	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	35	kV/mm	IEC 60243-1
^[C] Comparative tracking index	250	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.7	%	Sim. to ISO 62
^[C] Humidity absorption	0.2	%	Sim. to ISO 62
^[C] Density	1140	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	240	mm/s	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	95 - 110	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	260 - 280	°C	-
Mold temperature	70 - 90	°C	-
Zone 1	230 - 240	°C	-
Zone 2	235 - 245	°C	-
Zone 3	240 - 270	°C	-
Nozzle temperature	265 - 275	°C	-
Back pressure	5 - 15	MPa	-

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources, Biocompatibility ISO 10993, ISCC Plus

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa