

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	19	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	56.5	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	2344	MPa	ASTM D 790
Flexural Strength	87.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	641	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	104	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1150	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Chemical Resistance

General Chemical Resistance

### Regional Availability

North America

### Applications

Medical