

TRISTAR® PC-10FRN-(V) GY

PC

Amco Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	58.6	MPa	ASTM D 638
Elongation at Break	75	%	ASTM D 638
Flexural Modulus	2137	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	587	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	125	°C	ISO 75-1/-2
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	777	°C	IEC 60695-2-13
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.52	mm	-
Coefficient of Thermal Expansion, MD	70.2	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	68.4	E-6/K	ASTM D 696
DTUL @ 66 psi	134	°C	ASTM D 648
Limiting Oxygen Index	38	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	24	kV/mm	ASTM D 149
Volume Resistivity	3E15	Ohm*cm	ASTM D 257
Arc Resistance	90	s	ASTM D 495
Other Standards^[5]			
Comparative tracking index	325	-	UL 746A

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.18	%	ASTM D 570
Density	1230	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	282 - 304	°C	-
Mold temperature	71.1 - 93.3	°C	-
Zone 1	254 - 274	°C	-
Zone 2	266 - 277	°C	-
Zone 3	277 - 293	°C	-
Nozzle temperature	271 - 293	°C	-
Injection pressure	75.8 - 124	MPa	-
Back pressure	0.345 - 1.38	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Flame retardant, U.V. stabilized or stable to weather

Certifications

RoHS compliant

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa