

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	62.1	MPa	ASTM D 638
Elongation at Break	75	%	ASTM D 638
Flexural Modulus	2213	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	641	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	2.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	777	°C	IEC 60695-2-13

ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.52	mm	-
Coefficient of Thermal Expansion, MD	70.2	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	68.4	E-6/K	ASTM D 696
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	126	°C	ASTM D 648
Limiting Oxygen Index	38	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	24	kV/mm	ASTM D 149
Volume Resistivity	6E15	Ohm*cm	ASTM D 257
Arc Resistance	90	s	ASTM D 495
Other Standards^[5]			
Comparative tracking index	325	-	UL 746A

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	293 - 315	°C	-
Mold temperature	71.1 - 93.3	°C	-
Zone 1	265 - 285	°C	-
Zone 2	275 - 290	°C	-
Zone 3	287 - 303	°C	-
Nozzle temperature	282 - 303	°C	-
Screw speed	40 - 70	rpm	-
Injection pressure	68.9 - 124	MPa	-
Back pressure	0.345 - 1.38	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Flame retardant, Halogen-free, High impact or impact modified

Certifications

RoHS compliant

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa