

Eco Meblend IT65 BK

(PC+ABS)

Mepol S.r.l.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	46	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A
Izod notched impact strength	35	kJ/m ²	ISO 180/1A
Temperature	0	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	110	°C	ISO 75-1/-2
Vicat softening temperature, A	130	°C	ISO 306
Vicat softening temperature, B	118	°C	ISO 306
Other properties			
Water absorption	0.6	%	Sim. to ISO 62
Density	1130	kg/m ³	ISO 1183

Characteristics**Delivery form**

Black

Applications

General Purpose

Certifications

Recycled Resin Content

Regional Availability

Europe