

**Eco Meblend IT85 BK**

(PC+ABS)

Mepol S.r.l.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>15</b>	g/10min	ISO 1133
Temperature	<b>260</b>	°C	-
Load	<b>5</b>	kg	-
Molding shrinkage, parallel	<b>0.6</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>2400</b>	MPa	ISO 527
Yield stress	<b>50</b>	MPa	ISO 527
Strain at break	<b>&gt;50</b>	%	ISO 527
Flexural modulus, 23°C	<b>2400</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>50</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>40</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>0</b>	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>115</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>135</b>	°C	ISO 306
Vicat softening temperature, B	<b>126</b>	°C	ISO 306
<b>Other properties</b>			
Water absorption	<b>0.6</b>	%	Sim. to ISO 62
Density	<b>1140</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Black

**Special Characteristics**

High impact or impact modified

**Certifications**

Recycled Resin Content

**Applications**

General Purpose

**Regional Availability**

Europe