

Product Texts

25% Recycled Content

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	58.6	MPa	ASTM D 638
Tensile Strength at Break	54.5	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	70	%	ASTM D 638
Flexural Modulus	2620	MPa	ASTM D 790
Flexural Strength	91	MPa	ASTM D 790
Izod Impact notched, 1/8 in	587	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Certifications

Recycled Resin Content

Special Characteristics

Flame retardant

Regional Availability

North America

Features

Low Odor