

## Ecomass® Compound 1002ZD93

PEBA-MED(x)

DOMO Engineering Plastics

### Product Texts

Nontoxic alternative to Lead (Pb)

### Mechanical properties

	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	15	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	180	MPa	ISO 178
Izod notched impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1A

### Other properties

	Value	Unit	Test Standard
Density	8000	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Other Extrusion

#### Chemical Resistance

Radiation Resistance

#### Delivery form

Pellets

#### Regional Availability

North America

#### Features

EMI Attenuation/Shielding, Low Odor, Copolymer