

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	5.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	10	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	19.6	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Flexural Modulus	706.3	MPa	ASTM D 790
Flexural Strength	17.7	MPa	ASTM D 790
Izod Impact notched, 1/8 in	540	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	67	°C	ASTM D 648
DTUL @ 264 psi	41	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	1000	Ohm	ASTM D 257
<b>Other properties</b>			
Density	1050	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Blow Molding

### Regional Availability

Europe, Asia Pacific

### Special Characteristics

Increased electrical conductivity