

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Electric strength	22	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	935	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Zone 1	150	°C	-
Zone 2	170	°C	-
Zone 3	170	°C	-
Zone 4	170	°C	-
Nozzle temperature	170	°C	-

Characteristics

Processing
Other Extrusion

Chemical Resistance
Oxidation Resistance

Delivery form
Black

Applications
Electrical and Electronical

Special Characteristics
U.V. stabilized or stable to weather

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Features
Crosslinkable, Thermal Stability