

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	100	MPa	ISO 527
Flexural modulus, 23°C	4000	MPa	ISO 178
Izod notched impact strength, +23°C	7.6	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Other Extrusion

Applications

Medical

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific