

VICTREX® PEEK 650P

PEEK

Victrex plc

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3900	MPa	ISO 527
Yield stress	90	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	3600	MPa	ISO 178
Flexural strength	150	MPa	ISO 178
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	7.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.02	%	-
Melt temperature	380 - 400	°C	-

Characteristics**Processing**

Other Extrusion

Delivery form

Powder, Natural Color

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa