

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	27	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2270	MPa	ISO 527
Tensile Strength	46	MPa	ISO 527
Charpy impact strength, -30°C	10	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	32	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	32	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature, A	120	°C	ISO 306
Vicat softening temperature, B	110	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Gloss, 60°	90	-	ISO 2813

Other properties	Value	Unit	Test Standard
Density	1170	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	240 - 260	°C	-
Mold temperature	70 - 90	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	255	°C	-

## Characteristics

### Processing

Injection Molding, Other Extrusion

### Delivery form

Black

### Certifications

Recycled Resin Content, RoHS compliant

### Regional Availability

North America, Europe, Asia Pacific