

Matrixx FPE3A20CC

PE-GF20

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	41.4	MPa	ASTM D 638
Flexural Modulus	2760	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Other properties			
Density	1100	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Regional Availability

North America

Features

Chemically Coupled Reinforcement