

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	24	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	170	MPa	ISO 527
Tensile Strength	10	MPa	ISO 527
Strain at break	120	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	109	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-100	°C	ISO 11357-1/-2

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	200 - 240	°C	-
Mold temperature	30 - 60	°C	-
Zone 1	190 - 240	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Metal Detectable

Chemical Resistance

Radiation Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America