

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	130	MPa	ISO 527
Shore A hardness	90	-	ISO 7619-1
Other properties			
Density	980	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Film Extrusion, Profile Extrusion

Delivery form

Granules, Black

Additives

Lubricants

Special Characteristics

Anti-static, High impact or impact modified, U.V. stabilized or stable to weather

Features

Thermal Stability, Weldable, Copolymer

Chemical Resistance

Acid Resistance, Alkali Resistance, Environmental Stress Crack Resistance, Solvent Resistance

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa