

Product Texts

Filler: 30 % Hazelnut Shel

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

	Value	Unit	Test Standard
Melt flow index, MFI	14.3	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties**Value****Unit****Test Standard****ISO Data**

	Value	Unit	Test Standard
Tensile Modulus	2770	MPa	ISO 527
Strain at break	6.7	%	ISO 527
Charpy impact strength, +23°C	7	kJ/m ²	ISO 179/1eU

Characteristics**Processing**

Injection Molding

Applications

Packaging

Certifications

Contains renewable resources

Regional Availability

Europe