

**Product Texts**

Filler: 30 % Leather

**Processing/Physical Characteristics****Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI	<b>1.2</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

**Mechanical properties****Value****Unit****Test Standard****ISO Data**

Tensile Modulus	<b>1280</b>	MPa	ISO 527
Strain at break	<b>26.3</b>	%	ISO 527
Charpy impact strength, +23°C	<b>95</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Shore D hardness	<b>60</b>	-	ISO 7619-1

**Characteristics****Processing**

Injection Molding

**Applications**

Packaging

**Certifications**

Contains renewable resources

**Regional Availability**

Europe