

**Product Texts**

Filler: 30 % Cocoa shell

**Processing/Physical Characteristics****Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI

**9.8**

g/10min

ISO 1133

Temperature

**190**

°C

-

Load

**2.16**

kg

-

**Mechanical properties****Value****Unit****Test Standard****ISO Data**

Tensile Modulus

**1360**

MPa

ISO 527

Strain at break

**5.4**

%

ISO 527

Charpy impact strength, +23°C

**8.2**kJ/m<sup>2</sup>

ISO 179/1eU

**Characteristics****Processing**

Injection Molding

**Applications**

Packaging

**Certifications**

Contains renewable resources

**Regional Availability**

Europe