

HAC8270HF

(PC+ABS)

Shanghai Kumho Sunny Plastics Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	60	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	82	MPa	ASTM D 790
Izod Impact notched, 1/8 in	700	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 264 psi	114	°C	ASTM D 648
Vicat Temperature	128	°C	ASTM D 1525
Electrical properties			
ISO Data			
Volume resistivity	1E15	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Other properties			
Density	1150	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	260 - 290	°C	-
Mold temperature	60 - 90	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive, Electrical and Electronical

Regional Availability

Asia Pacific