



**ULTEM™ Resin SF2250EPR**

PEI-GF20

Saudi Basic Industries Corporation (SABIC)

Mold temperature	<b>135 - 165</b>	°C	-
Zone 1	<b>330 - 400</b>	°C	-
Zone 2	<b>345 - 400</b>	°C	-
Zone 3	<b>345 - 400</b>	°C	-
Screw speed	<b>40 - 70</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific