

Product Texts

30% Glass fiber filled, standard flow Polyetherimide (Tg 217C). Meets FAR 25.853 and OSU 65/65 with low toxicity, smoke, and flame evolution. ECO Conforming.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4.2	g/10min	ASTM D 1238
Temperature	337	°C	-
Load	6.6	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	8960	MPa	ASTM D 638
Tensile Strength at Break	155	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1490	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	365 - 390	°C	-
Mold temperature	135 - 165	°C	-
Zone 1	345 - 365	°C	-
Zone 2	355 - 375	°C	-
Zone 3	365 - 390	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

Asia Pacific