



**ULTEM™ Resin 2410EPR - Asia**

PEI-GF40

Saudi Basic Industries Corporation (SABIC)

Humidity absorption	<b>0.4</b>	%	Sim. to ISO 62
Density	<b>1560</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1560</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>150</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>350 - 400</b>	°C	-
Mold temperature	<b>135 - 165</b>	°C	-
Zone 1	<b>330 - 400</b>	°C	-
Zone 2	<b>340 - 400</b>	°C	-
Zone 3	<b>345 - 400</b>	°C	-
Screw speed	<b>40 - 70</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Asia Pacific