

G-PAEK™ 1100P

PEK

Gharda Plastics Limited

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 264 psi	167	°C	ASTM D 648
Melting Temperature	372	°C	ASTM D 3418
Glass Transition Temperature	152	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Bulk Density	300	kg/m ³	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

Flame retardant

Delivery form

Powder, White

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa