

RTP 2207 A

PEK-GF

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	15170	MPa	ASTM D 638
Tensile Strength	207	MPa	ASTM D 638
Flexural Modulus	13790	MPa	ASTM D 790
Flexural Strength	310	MPa	ASTM D 790
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-

Other properties	Value	Unit	Test Standard
Density	1650	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	179	°C	-
Pre-drying - Time	2	h	-
Mold temperature	179 - 218	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific