

INFINO HR-1008B

(PC+ABS)

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	60	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	10	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	62	MPa	ASTM D 638
Flexural Modulus	2600	MPa	ASTM D 790
Flexural Strength	86	MPa	ASTM D 790
Izod Impact notched, 1/8 in	490	J/m	ASTM D 256
Thermal properties			
ISO Data			
Vicat softening temperature, B	117	°C	ISO 306
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	105	°C	ASTM D 648
Other properties			
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific