

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	13100	MPa	ASTM D 638
Tensile Strength	193	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	11700	MPa	ASTM D 790
Flexural Strength	262	MPa	ASTM D 790
Rockwell Hardness	M 103	-	ASTM D 785
Izod Impact notched, 1/8 in	0.08	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Coefficient of Thermal Expansion, MD	16	E-6/K	ASTM D 696
DTUL @ 264 psi	321	°C	ASTM D 648
Melting Temperature	360	°C	ASTM D 3418
Glass Transition Temperature	163	°C	ASTM E 1356
Electrical properties			
ASTM Data			
Volume Resistivity	2.5E16	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.04	%	ASTM D 570
Density	1520	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets, White

Regional Availability

North America, Europe, Asia Pacific