LNP™ COLORCOMP™ Compound J1000

PESU | Saudi Basic Industries Corporation (SABIC)

Product Texts

LNP COLORCOMP J1000 compound is based on unfilled Polyethersulfone (PES) resin.

UL Yellow Card Link E121562-101282575

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**2700**	MPa	ISO 527
Yield stress	**91**	MPa	ISO 527
Yield strain	**6.8**	%	ISO 527
Stress at break	**67**	MPa	ISO 527
Flexural modulus	**2600**	MPa	ISO 178
Izod impact strength, +23°C, 4mm	**N**	kJ/m²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	**7**	kJ/m²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	**201**	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	**216**	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	**59**	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	**59**	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	**V-0**	class	IEC 60695-11-10
Thickness tested	**0.5**	mm	-

Other properties	Value	Unit	Test Standard
Density	**1370**	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**120 - 150**	°C	-
Pre-drying - Time	**4**	h	-
Processing humidity	**≤0.05**	%	-
Melt temperature	**355 - 370**	°C	-
Mold temperature	**140 - 150**	°C	-
Zone 1	**345 - 355**	°C	-
Zone 2	**360 - 370**	°C	-
Zone 3	**370 - 380**	°C	-
Screw speed	**60 - 100**	rpm	-
Back pressure	**0.3 - 0.7**	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Applications

Automotive

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.