

Product Texts

LNP COLORCOMP J1000-WH9G618 compound is based on Polyethersulfone (PES) resin. Added features of this grade include: Extrusion, Customer Specific Color.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	85	MPa	ISO 527
Strain at break	1.6	%	ISO 527
Flexural modulus	2800	MPa	ISO 178
Izod impact strength, +23°C, 4mm	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Coeff. of linear therm. expansion, parallel	58	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	62	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1380	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	355 - 370	°C	-
Mold temperature	140 - 150	°C	-
Zone 1	345 - 355	°C	-
Zone 2	360 - 370	°C	-
Zone 3	370 - 380	°C	-
Screw speed	60 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Applications

Automotive