

**INFINO NH-1000T**

(PC+ABS)

Lotte Chemical Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>39</b>	g/10min	ISO 1133
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>39</b>	g/10min	ASTM D 1238
Temperature	<b>220</b>	°C	-
Load	<b>10</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>2500</b>	MPa	ISO 527
Yield stress	<b>54</b>	MPa	ISO 527
Stress at break	<b>44</b>	MPa	ISO 527
Strain at break	<b>78</b>	%	ISO 527
Flexural modulus, 23°C	<b>2700</b>	MPa	ISO 178
Flexural strength	<b>81</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>39</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	<b>35</b>	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	<b>R 114</b>	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>54</b>	MPa	ASTM D 638
Flexural Modulus	<b>2400</b>	MPa	ASTM D 790
Flexural Strength	<b>77</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 112</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>390</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>76</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>86</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>89</b>	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	<b>V-1</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Burning behav. at thickness h	<b>V-2</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-
Burning behav. 5V at thickness h	<b>5VB</b>	class	IEC 60695-11-20
Thickness tested	<b>2.0</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-
<b>Other properties</b>			
Density	<b>1170</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1170</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Processing humidity	<b>≤0.05</b>	%	-
Melt temperature	<b>260</b>	°C	-
Mold temperature	<b>50 - 70</b>	°C	-
Zone 1	<b>220 - 230</b>	°C	-
Zone 2	<b>240 - 250</b>	°C	-
Zone 3	<b>260 - 270</b>	°C	-
Nozzle temperature	<b>270</b>	°C	-
Screw speed	<b>50 - 150</b>	rpm	-

**INFINO NH-1000T**

(PC+ABS)

Lotte Chemical Corporation

Injection pressure	<b>59 - 210</b>	MPa	-
Back pressure	<b>0.5 - 2</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific

**Delivery form**

Pellets, Natural Color