

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	49	E-6/K	ASTM D 696
Glass Transition Temperature	220	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.6	%	ASTM D 570
Density	1370	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Coating, Spray and Pour

### Delivery form

Granules, Powder

### Special Characteristics

Flame retardant, Heat stabilized or stable to heat, Transparent

### Features

Creep Resistance, Good Adhesion, Thermal Stability

### Chemical Resistance

Acid Resistance, General Chemical Resistance, Hydrolytically Stable

### Certifications

Food contact

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa