

INFINO NH-1001T

(PC+ABS)

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Stress at break	52	MPa	ISO 527
Strain at break	99	%	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Flexural strength	83	MPa	ISO 178
Charpy notched impact strength, +23°C	60	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	55	kJ/m ²	ISO 180/1A
Rockwell hardness	R 114	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2300	MPa	ASTM D 638
Tensile Strength at Yield	57	MPa	ASTM D 638
Tensile Strength at Break	52	MPa	ASTM D 638
Elongation at Break	87	%	ASTM D 638
Flexural Modulus	2200	MPa	ASTM D 790
Flexural Strength	78	MPa	ASTM D 790
Rockwell Hardness	R 114	-	ASTM D 785
Izod Impact notched, 1/8 in	640	J/m	ASTM D 256
Izod Impact notched, 1/4 in	520	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	77	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	88	°C	ISO 75-1/-2
Vicat softening temperature, B	93	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	2.0	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	2	mm	-
DTUL @ 66 psi	90	°C	ASTM D 648
DTUL @ 264 psi	84	°C	ASTM D 648
Other properties			
Value			
Density	1160	kg/m ³	ISO 1183
Density	1160	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Value			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.05	%	-
Melt temperature	260	°C	-
Mold temperature	50 - 70	°C	-
Zone 1	220 - 230	°C	-
Zone 2	240 - 250	°C	-
Zone 3	260 - 270	°C	-

INFINO NH-1001T

(PC+ABS)

Lotte Chemical Corporation

Nozzle temperature	270	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	93	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color