

**Veradel® A-304P**

PESU

Syensqo

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	<b>49</b>	E-6/K	ASTM D 696
Glass Transition Temperature	<b>220</b>	°C	ASTM E 1356

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water Absorption, 24hr	<b>0.6</b>	%	ASTM D 570
Density	<b>1370</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Film Extrusion, Coating, Spray and Pour

**Delivery form**

Powder

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat, Transparent

**Features**

Creep Resistance, Good Adhesion, Thermal Stability

**Chemical Resistance**

Acid Resistance, General Chemical Resistance, Hydrolytically Stable

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa