

RTP 1482 N

PESU-CF

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.001	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	12410	MPa	ASTM D 638
Tensile Strength	172	MPa	ASTM D 638
Flexural Modulus	11720	MPa	ASTM D 790
Flexural Strength	234	MPa	ASTM D 790
Izod Impact notched, 1/8 in	58.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	210	°C	ASTM D 648
Electrical properties			
ASTM Data			
Volume Resistivity	100000	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.42	%	ASTM D 570
Density	1420	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	343 - 377	°C	-
Mold temperature	135 - 177	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific