

INFINO NH-1015S

(PC+ABS)

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	36	g/10min	ISO 1133
Temperature	250	°C	-
Load	10	kg	-
ASTM Data			
Melt Flow Index, MFI	36	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0055	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Yield stress	61	MPa	ISO 527
Stress at break	48	MPa	ISO 527
Strain at break	27	%	ISO 527
Flexural modulus, 23°C	2550	MPa	ISO 178
Flexural strength	89	MPa	ISO 178
Charpy notched impact strength, +23°C	27	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	35	kJ/m ²	ISO 180/1A
Rockwell hardness	R 121	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2400	MPa	ASTM D 638
Tensile Strength at Yield	59	MPa	ASTM D 638
Tensile Strength at Break	47	MPa	ASTM D 638
Elongation at Break	26	%	ASTM D 638
Flexural Modulus	2400	MPa	ASTM D 790
Flexural Strength	85	MPa	ASTM D 790
Rockwell Hardness	R 121	-	ASTM D 785
Izod Impact notched, 1/8 in	390	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	510	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	84	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, B	100	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	1.2	mm	-
Burning behav. 5V at thickness h	5VB	class	IEC 60695-11-20
Thickness tested	2.0	mm	-
ASTM Data			
UL 94 Flame rating	V-1	-	UL 94
Thickness tested	1.2	mm	-
DTUL @ 66 psi	96	°C	ASTM D 648
DTUL @ 264 psi	92	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ISO 1183
Density	1180	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-

INFINO NH-1015S

(PC+ABS)

Lotte Chemical Corporation

Processing humidity	≤0.05	%	-
Melt temperature	260	°C	-
Mold temperature	50 - 70	°C	-
Zone 1	220 - 230	°C	-
Zone 2	240 - 250	°C	-
Zone 3	260 - 270	°C	-
Nozzle temperature	270	°C	-
Screw speed	50 - 150	rpm	-
Injection pressure	98	MPa	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Applications

IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific