

INFINO NH-1015U

(PC+ABS)

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	34	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	34	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Stress at break	56	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Charpy notched impact strength, +23°C	45	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	40	kJ/m ²	ISO 180/1A
Rockwell hardness	R 118	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2400	MPa	ASTM D 638
Tensile Strength at Yield	59	MPa	ASTM D 638
Tensile Strength at Break	55	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	2500	MPa	ASTM D 790
Flexural Strength	88	MPa	ASTM D 790
Rockwell Hardness	R 118	-	ASTM D 785
Izod Impact notched, 1/8 in	540	J/m	ASTM D 256
Izod Impact notched, 1/4 in	180	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	82	°C	ISO 75-1/-2
Vicat softening temperature, B	98	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	86	°C	ASTM D 648
Other properties			
Density	1180	kg/m ³	ISO 1183
Density	1180	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	270	°C	-

INFINO NH-1015U

(PC+ABS)

Lotte Chemical Corporation

Mold temperature	50 - 90	°C	-
Zone 1	230 - 240	°C	-
Zone 2	250 - 260	°C	-
Zone 3	260 - 270	°C	-
Nozzle temperature	270	°C	-
Screw speed	50 - 100	rpm	-
Injection pressure	98	MPa	-
Back pressure	0.5 - 2.9	MPa	-

Characteristics**Processing**

Injection Molding

Applications

IT / Business Machine

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific